



INVESTMENT CASTING WITH 14K Ni WHITE GOLD

GR14W601000



Developed for use as casting grain, Imperial's 14K Nickel White grain is formulated to provide a whiter colour while offering superior casting characteristics, ductility for settings and a surface hardness that promotes easier finishing. Imperial's family of 14K Ni-White casting alloys already are classed in the Grade 1 (whitest) class, in accordance to the new standard for whiteness established by the World gold Council and MJSA (*).



(* Please refer to www.imperialproducts.com/quality for more information regarding white gold classification



CASTING INFORMATION

1. **Melting range:** *1000 - 1030°C / *1832 - 1886°F (*solidus temperatures are estimates)
2. **Density:** 12.73 grams/cm³ , 134.3 dwt/in³
3. **Recommended Casting and Flask Temperatures:** These vary with the design and mass of the item(s) being cast, so you may need to run some test casts to work out the combination of temperatures best suited to your specific design. As a starting point, we recommend the following conditions:

	<u>Casting Temperature</u>	<u>Flask Temperature</u>
Large Items	1060°C / 1940°F	480°C / 900°F
Medium sized items	1090°C / 1995°F	540°C / 1000°F
Small, intricate items	1130°C / 2065°F	590°C / 1100°F

4. **Cooling:** After casting, let the flask cool at room temperature until it is no longer red (approximately 10 minutes), then quench in water.
5. **Recycling:** This product can be recycled 50% reused / 50% new grain, under strictly clean casting procedures to avoid carryover of contaminants (investment material, etc.).
6. **Physical Properties:**

Ultimate Tensile Strength (UTS): 97,000 psi
As-Cast Hardness (Vickers): 185 Hv

We are always interested in hearing your opinion of how our products have performed for your application. Also, contact us should you have any questions, comments or require information regarding Imperial's wide range of gold, silver and platinum products.

Imperial's Precious Metals
Inspiring Trust



IMPERIAL SMELTING AND REFINING CO. OF CANADA LTD. — WWW.IMPERIALPRODUCTS.COM

TORONTO HEAD OFFICE & PLANT: 451 Denison St., Markham, ON L3R 1B7 Canada
 Phone 905-475-9566 • Toll-Free 1-800-263-1669

VANCOUVER: 602 West Hastings Street, Suite 614, Vancouver, BC V6B 1P2
 Phone 604-685-2344 • Toll-Free 1-800-663-0455

RHODE ISLAND: 40 Bay State Ave., Warwick, RI 02888
 Phone 401-739-5060 • Toll-Free 1-877-795-5060

14KW 601 Grain